

# MirrorEffect AntiScratch ASLAN SE 75

## The highly reflective, scratch-resistant mirror effect film

This self-adhesive polyester film is characterized by a high-quality mirror like effect. Applied on even substrates, the surface of the film reflects mirror images brilliantly, and makes rooms appear optically larger and brighter. The high scratch-resistance of the film ensures that the mirror effect remains brilliant in the long term. Since the mirror effect can be seen on both sides, the film particularly shows to advantage, when it is applied behind glass. Especially designed for the decoration of smooth surfaces, the self-adhesive mirror effect film is ideally suited for applications in exhibition stand construction, shop fitting, visual merchandising, interior design etc.

For any further information please contact our technical advisory service:  
**+49 (0) 2204.708-80**

## Construction

face film:	polyester	
thickness:	~ 75 µm	
adhesive:	acrylic pressure sensitive adhesive	square quantity: ~ 20 g/m <sup>2</sup>
release liner:	PET	square weight: ~ 140 g/m <sup>2</sup>

## Characteristics

adhesive strength: (ASTMD-903)	immediately:	~ 1.5 N/25 mm
	after 1 week:	~ 10 N/25 mm
temperature:	application temperature:	min. 15°C
	service temperature range:	-30 °C up to +80 °C
minimum durability:	3-5 years outdoors, with vertical exposure, in central European standard climatic conditions	

**ASLAN, Schwarz GmbH & Co. KG**

Oberauel 2 · 51491 Overath · Germany

phone +49 (0) 2204.708 80 · fax +49 (0) 2204.708 50

e-mail [info@ASLAN-Schwarz.com](mailto:info@ASLAN-Schwarz.com)



[www.ASLAN-Schwarz.com](http://www.ASLAN-Schwarz.com)

**ASLAN**®

EXPERTISE IN SELF-ADHESIVE FILMS

# MirrorEffect AntiScratch ASLAN SE 75

## Processing

### digital cutting:

The self-adhesive film is ideally suited for cutting. The vertical height of capital letters should not be smaller than 10 mm. When cutting the self-adhesive film, the pen pressure should be set a higher and a cutter blade for thicker materials should be chosen.

### application:

The film is to be applied dry.

A wet application is possible to a limited extent, in consideration and compliance of our separate processing instructions for wet applications.

MirrorEffect AntiScratch ASLAN SE 75 is exclusively suited for smooth, even, non-elastic and non-curved surfaces. The film must not be applied on outgassing surfaces like non-tempered acrylic glass, since bubbles might occur, particularly under short-term exposure to heat.

To bring out the mirror effect as ideally as possible, the substrate should be absolutely smooth and homogenous as well as free of dust, grease and lint. To minimize an electrostatic charge during the application, the humidity of the working environment should be increased and machines, e. g. laminators, should be grounded (please also see our separate tips on reducing electrostatics).

Due to the high scratch-resistance of the film's surface, the film can be applied to large areas without the need to over-laminate it with an additional protective film.

For the application of letterings etc. we recommend the application tape LowTackTape ASLAN TP 110.

Edges of the film can be protected against humidity and environmental conditions by sealing them with a suitable edge sealing compound.

### film surface:

Tiny surface defects like spots and matt stripes as well as slight optical distortions are due to technical reasons and comply with the standard quality.

### cleaning:

The film can be cleaned with a microfiber cloth or commercially available cleaning agents. Cleaning aids or agents used should be non-abrasive and free of aggressive solvents.

### storage life:

Before application, the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

### State: 10|2016

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberaue 2 · 51491 Overath · Germany

phone +49 (0) 2204.708 80 · fax +49 (0) 2204.708 50

e-mail [info@ASLAN-Schwarz.com](mailto:info@ASLAN-Schwarz.com)



[www.ASLAN-Schwarz.com](http://www.ASLAN-Schwarz.com)

**ASLAN**

EXPERTISE IN SELF-ADHESIVE FILMS